



S.C. RAFINĂRIA STEAUA ROMÂNĂ S.A.

CÂMPINA, CALEA DOFTANEI NR. 15, 2150
Prahova, ROMÂNIA

Tel: (+40) 244 336 151 ♦ Fax: (+40) 2 44 337 341
E-mail: steauaromana@steauaromana.ro; www.steauaromana.ro



Bitum H 45 ST 5 / 2005

UTILISATION: FOR PRODUCING THE HYDROINSULANTED MATERIALS USED IN THE BUILDING MATERIALS INDUSTRY

CHARACTERISTICS	QUALITY TECHNICAL CONDITIONS	TEST METHOD	
		STAS	ASTM
Heat point, IB, °C, max.	45	SR EN 1427/2002	D 127/87
Flammability M, °C min.	280	5489-80	D 92/97
Penetration at 25°C, 1/10mm, min.	180	SR EN 1426/2002	D217/94
Ductility, la 25°C, cm. min.	10	SR 61-96	D113
Soluble substance in carbon dichloride %, min.	99	115/80	-
Water, %	traces	24/2-89	D 95/83